


ArmorLiner® 30

15 OZ GEOMEMBRANE



PRODUCT DESCRIPTION

A heavyweight fabric incorporating a special weave pattern to enhance puncture, flatness, and tear properties. The coating recipe is designed to improve toughness and abrasion resistance for exposed applications up to 15 years.

RECOMMENDED APPLICATIONS

Large Exposed Reservoirs, Water Ski Lakes, Long Term Containment Liners

PRODUCT DIMENSIONS

Cores 4 inch I.D. or 5 inch I.D. available (10 cm or 13 cm)
Width Up to 150 in (381 cm) (-0, +0.5) as ordered
Length Minimum 250 yds/roll (229 m); up to 1000 yds/roll (914 m)

PRODUCT SPECIFICATIONS

Weave Woven black HDPE scrim
Coating LDPE, 5.25 mil average each side (126 g/m²/side)
Color White, black or other colored coatings available
Weight 15 oz/yd² (509 g/m²) ± 5%



Certified to
NSF/ANSI/CAN 61

These values are typical data and are not intended as limiting specifications.

PERFORMANCE PROPERTIES

The following data are typical values based on ASTM standard tests. This data should not be considered specification.

Thickness ASTM D1777	Nominal 30 mil (0.75mm), ± 10%
Grab Tensile (N) ASTM D7004	MD 425 lb (1890) TD 510 lb (2268)
Strip Tensile (N/5cm) ASTM D7003	MD 265 lb/in (2320) TD 330 lb/in (2889)
Tongue Tear—large scale (N) ASTM D5884	MD 65 lb (289) TD 75 lb (334)
Mullen Burst ASTM D751	765 psi (5279 kPa)
MVTR ASTM E96 Proc. BW	0.089 g/m ² · 24hr (0.013 perms)
Hydraulic Conductivity (Permeability) Calculated from MVTR	4.59 x 10 ⁻¹⁵ cm/s
Hydrostatic Resistance ASTM D751	610 psi (4203 kPa)
Puncture Resistance ASTM D4833	225 lb (1001 N)
CBR Static Puncture ASTM D6241	1481 lb (6576 N)
Carbon Black Content ASTM D4218	3 %
Dimensional Stability ASTM D1204	MD -2.2% TD -1.4%
Low Temperature Flex ASTM D2136	MD & TD: Pass @ -65°C (-85°F)
HP-OIT ASTM D5885 (Measured on coating formulation)	2410 minutes
Accelerated UV Weatheringⁱ ASTM G151 ASTM G154	>90 % strength retention after 2000 hrs exposure @ 0.77 W/m ² /nm, or 1200 hrs exposure @ 1.35 W/m ² /nm

MD = Machine Direction. TD = Transverse Direction
ⁱ Q.U.V [A-340 Lamps]; 8 hrs UV @ 60°C; 4 hrs condensation @ 50°C



Certified to
NSF/ANSI/CAN 61

These values are typical data and are not intended as limiting specifications.

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.